



technical data sheet

BOSTIK COLOUR SEAL

Acrylic Joint Sealant

PRODUCT

Bostik Colour Seal is a high performance acrylic gap filler and joint sealant.

DESCRIPTION

Bostik Colour Seal is a strong, highly flexible (total 20-25%), anti-fungal, mildew resistant acrylic gap filler. Colour Seal is designed for internal and external applications for horizontal and vertical sealing requirements where a flexible sealant is required. **Bostik Colour Seal** offers excellent adhesion properties when cured and is more flexible than conventional acrylic gap sealants with minimal shrinkage.

RECOMMENDED USES

- Bathroom, kitchen and laundry.
- Sealing gaps in plasterboard, brickwork, timber, concrete, cement sheet and ceramic tiles.
- May be painted with conventional available paints.
- Window and door perimeter sealing

FEATURES & BENEFITS

- Anti-fungal
- Extensive colour range available.
- Good adhesion to most building materials
- May be overpainted
- Excellent flexible properties
- Water based technology, water clean up
- Non slump
- Interior/exterior
- Australian made

TYPICAL PROPERTIES

| | |
|---------------------------------|--------------------------------|
| Appearance | Smooth, paste like consistency |
| Colour | Various |
| Chemical Type | Water based acrylic |
| Specific Gravity | 1.5 |
| Service Temperature | -20°C to +75°C |
| Tack Free Working Time | 15mins @ 20°C |
| Total Max Joint Movement | Up To 20% |
| Max Joint Width | 25mm. |

Results are after seven days cure @ 25°C and 50%RH.

PACKAGING

Bostik Colour Seal is available in 440gm cartridges in cartons of 12.

APPLICATION INSTRUCTIONS

Preparation:

Clean all surfaces by removing foreign matter and contaminants such as oil, dust, grease, frost, water, surface dirt, oil sealant and any protective coating. Cut tip off cartridge. Cut nozzle to desired size at 45° angle. Screw nozzle onto cartridge. Place cartridge into caulking gun.

Hold gun at 45° angle with nozzle in contact with both sides of joint.

Apply by pushing sealant ahead of the nozzle, thus ensuring filler is pushed firmly into place. Remove excess filler with a wet putty knife or damp cloth. **Bostik Colour Seal** becomes touch dry within 30 minutes under ambient conditions. For best results when painting allow 72 hours prior to painting (allow longer curing time in cool or damp conditions).

PRECAUTIONS

Not recommended for use

- Where abrasion or physical abuse can be expected.
- In sealing submerged joints
- Underwater or in marine applications
- When applied to substrates below 5°C
- With absorptive surfaces such as marble, limestone or granite without prior testing for staining and/or discolouration.
- On powder coated surfaces
- On damp substrates
- On trafficable applications.
- External expansion joints
- Where joint movement is excessive (greater than 20% total joint movement).
- Where exposed to water or where water pools.

P.A.T.S (Pretested Adhesion To Substrate) Programme

Bostik offer a service in which a program has been established to eliminate potential field problems by pre-testing Bostik adhesives with samples of building materials to which the adhesive will be applied. This service is available on large projects where pre-application testing will aid in determining the proper surface preparation method to achieve optimum adhesion. Consult a Bostik representative for further information.

SAFETY DIRECTIONS

- Avoid contact with skin and eyes. If contact occurs, wash area with large quantities of water. Wear gloves for prolonged or repeated exposure.
- For more detailed information refer to Material Safety Data Sheet.

CLEAN-UP

Clean up uncured material and equipment with water immediately after using. For removal on skin, uncured sealant can be removed with Bostik Handi-Clean towels.

STORAGE

Store between 5°C and 30°C. Shelf life is a minimum of twelve months in original unopened cartridge.

FIRE

Bostik Colour Seal is non-flammable

BOSTIK COLOUR SEAL

| ITEM NO. | COLOUR | STOCK SIZE |
|----------|-----------------|-----------------|
| 268607 | Terracotta | 440gm Cartridge |
| 268593 | Vanilla | 440gm Cartridge |
| 268577 | White | 440gm Cartridge |
| 268615 | Beige | 440gm Cartridge |
| 268623 | Light Grey | 440gm Cartridge |
| 268585 | Dark Grey | 440gm Cartridge |
| 269999 | Black | 440gm Cartridge |
| 260007 | Coffee | 440gm Cartridge |
| 285463 | Chocolate Brown | 440gm Cartridge |
| 285455 | Deep Green | 440gm Cartridge |

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF BOSTIK AUSTRALIA PTY LTD

FOR FURTHER INFORMATION

BOSTIK AUSTRALIA PTY LTD
Phone: +61-3-9279 9333
Fax: +61-3-9279 9240

BOSTIK NZ LIMITED
Phone: +64-4-567 5119
Fax: +64-4-567-5412

BOSTIK SINGAPORE PTE LTD
Phone: +65 6863 4088
Fax: +65 6863 4077

BOSTIK (MALAYSIA) SDN BHD
Phone: +606 764 3246
Fax: +606 764 3248

SYDNEY
Phone: 02 8825 3488
Fax: 02 8825 3411

ADELAIDE
Phone: 08 8244 0511
Fax: 08 8244 0522

PERTH
Phone: 08 9258 6218
Fax: 08 9258 7687

BRISBANE
Phone: 07 3260 2206
Fax: 07 3260 2123

(ABN 79 003 893 838)

| | |
|--------------|-------------|
| Product: | Colour Seal |
| Issue Date: | March 2002 |
| Issue No: | 2 |
| Division: | Hardware |
| Total Pages: | 2 |