


TROWEL APPLIED FINISHING UNDERLAY

PACKAGING




MIXING



APPLICATION



USES



SUBSTRATES

CONCRETE, WOOD
TERRAZZO AND
CERAMIC TILED
FLOORS

DESCRIPTION

A cement based rapid setting trowel applied finishing underlay designed to smooth ridges, grooves, joints and gaps in the floor. Apply 0-3mm thick prior to installing a floor covering.

USES

Feather finish irregular floors. Designed to smooth grooves, joints, gaps and grout joint lines over concrete, wood, terrazzo and ceramic tiles.

FEATURES

- Exceptional bond strength.
- No primer required.
- Can be feather edged.
- Rapid setting.

COVERAGE (Approximate)

15-30m²/5kg bag depending on the surface condition.

PERFORMANCE DATA

	1 Day	7 Days	28 Days
Compression Strength (BS.4551) MPa	12.3	19.1	22.0
Tensile Strength (BS.4551) MPa	2.8	3.0	4.0
Hardness Brinnell	47.0	53.0	68.0
Adhesion to Substrate (Concrete)	1.8 Mpa		

SPECIFICATION

The finishing compound shall be a rapid setting trowel applied finishing underlay with a minimum compression strength of 22Mpa such as FEATHER FLOOR manufactured by Construction Chemicals and be applied in accordance with the manufacturer application instructions.

PREPARATION

Surfaces must be be structurally sound, solid and clean of waxes, sealers, curing compounds, dust, oil or any contaminant which act as a bond breaker. Floors with a moisture problem should be treated with EPECRETE before applying FEATHER FLOOR.

RECOMMENDED TOOLS

Mixing bucket, margin trowel and a steel trowel. For best results use a slow speed drill.

MIXING

The recommended mixing ratio is two parts by volume of powder to one part water. Additional water will weaken FEATHER FLOOR and will result in increased hardening times. Place the water into the container first and then add the powder while mixing by hand to a lump free consistency. Mechanical mixing with an electric drill will produce a creamier and smoother consistency without the need for additional water.

APPLICATION

FEATHER FLOOR is easily applied to any prepared surface using a steel trowel. Apply sufficient pressure to fill all defects and to feather the product into the subfloor surface. It is not necessary to leave a minimum thickness of the product on the substrate. Use the least amount possible to obtain the desired smoothness. The installation of the FEATHER FLOOR can also be made at any thickness in small, well-defined areas such as thresholds and height transitions between precast panels and where walls have been removed.

POT LIFE

Approximately 15-20 minutes at 20°C, but will vary with ambient temperature. If the material begins to set in the bucket, vigorous mixing may re-temper the product. (For best results use mechanical mixing).
DO NOT ADD MORE WATER.

LIMITATIONS

FEATHER FLOOR is intended for interior use only. Do not use in areas subject to standing water. Do not install on substrate of ambient temperatures below 10°C.

SAFETY PRECAUTIONS

Non-toxic. Contains cement which contains Silica. Wear gloves and appropriate respirator.

SHELF LIFE

1 Year.



- **ADELAIDE** 467 - 469 SOUTH RD REGENCY PARK 5010 PH: (08) 8346 8013 FAX: (08) 8340 2052
- **BRISBANE** 45 COULSON ST WACOL 4076 PH: (07) 3271 2944 FAX: (07) 3271 3892
- **MELBOURNE** 11 GABRIELLE CT BAYSWATER NORTH 3153 PH: (03) 9761 4711 FAX: (03) 9761 4748
- **PERTH** 11 COLLIE RD WELSHPOOL 6106 PH: (08) 9356 9999 FAX: (08) 9356 9955
- **SYDNEY** 31 NEWTON RD WETHERILL PARK 2164 PH: (02) 9756 3533 FAX: (02) 9756 3534
- **AUCKLAND** 16 CARPENTER RD EAST TAMAKI PH: (09) 273 5444 FAX: 0800 266 236
- **KUALA LUMPUR** LOT 2 JALAN KECAPI 33/2 ELITE INDUSTRIAL ESTATE OFF JALAN BUKIT KEMUNING 40000 SHAH ALAM PH: (603) 5122 2522 FAX: (603) 5122 2526