



Keralastic and Keralastic T



Two-component, high performance, polyurethane adhesives for ceramic tiles and stone material

CLASSIFICATION IN COMPLIANCE WITH EN 12004

Keralastic is an improved (2) reaction resin adhesive (R) as class R2.

Keralastic T is an improved (2) reaction resin adhesive (R) and slip resistant (T) as class R2T.

WHERE TO USE

Indoor and outdoor, wall and floor bonding of ceramic tiles, stone material and mosaics of all types on:

- screeds, renders, concrete, asphalt, wood, metal, PVC, reinforced polyester, asbestos-cement, gypsum, gypsum board, gypsum panels, etc.

Some application examples

- Bonding ceramic tiles, stone material and all types of mosaics in showers and on sheets used for prefabricated bathrooms.
- Bonding ceramic tiles and mosaics on wooden work surfaces or kitchens in order to achieve a waterproof substrate.
- Bonding ceramic tiles, stone material and mosaics on balconies, external terraces, flat roofs subject to foot traffic or domes.
- Bonding natural stones and reconstructed stone (marble of every type, slate, etc.) also subject to movement and size variation due to the absorption of water (class C of size stability according to Mapei standards).
- Bonding ceramic tiles and stone material on surfaces subject to vibrations and deflections.

TECHNICAL CHARACTERISTICS

Keralastic and **Keralastic T** are two-component solvent and water free adhesives which are flexible and waterproof. They are made up of a polyurethane base (Part A) and a special hardener (Part B).

On mixing the two parts together, the result is a paste with the following properties:

- easy workability;
- excellent durability and resistant to ageing;
- perfect adhesion on all surfaces used in building;
- hardens by chemical reaction without shrinkage (until it becomes highly resistant);
- high deformability;
- in the case of **Keralastic T**, highly thixotropic: it can be applied vertically without slump and without letting even heavy or large tiles slip. The slipping strength is in compliance with EN 1308.

RECOMMENDATIONS

- Do not use on very damp surfaces or where there is a risk of rising damp.
- The packs are pre-measured, therefore mixing errors are impossible. Do not use partial quantities. A wrong mixing ratio could cause damage during the curing process.
- Use the products in temperatures between +10°C and +30°C.



Keralastic Keralastic T

- In case of use on surfaces subject to continuous immersion in water, consult the Mapei technical services beforehand.

APPLICATION PROCEDURE

Preparing the substrates

The substrates must be cured, mechanically strong, free of loose particles, grease, oil, paint, wax and be sufficiently dry.

Cement substrates must not be subject to shrinkage after the installation of the tiles. During spring and summer renders must be cured for at least one week for every centimetre of thickness and cementitious screeds must be cured for at least 28 days, unless they have been made with MAPEI special binders for screeds such as **Mapecem**, **Mapecem Pronto**, **Topcem** or **Topcem Pronto**. Where this is not observed, the adhesion of **Keralastic** and **Keralastic T** to the substrate will be greatly compromised.

Rust on iron surfaces must be removed by sandblasting. It is recommended to reinforce gypsum, gypsum board and anhydrite substrates with a coat of **Primer EP** or **Mapeprim SP**.

Preparing the mix

The two components of **Keralastic** and **Keralastic T** are supplied in ready-to-mix cans:

- Part A: grey or white, 94 parts by weight;
- Part B: transparent straw, 6 parts by weight.

The ratio of the resin (part A) and the hardener (part B) is fixed and any modification could cause incorrect hardening of the product.

Pour the hardener (part B) into part A and mix well until a uniform grey or white paste is obtained. It is advisable to use a low speed electric stirrer to ensure perfect mixing and avoid overheating the mix, which would reduce the working time. Use the mix within 50-60 minutes of mixing.

Applying the mix

Apply on the substrate a uniform layer of **Keralastic** or **Keralastic T** with a notched trowel. Choose a trowel that will give a coverage to the back of the tiles of at least 65-70% (see "consumption").

For exterior installations, the tile backs must be completely covered with the adhesive. When both waterproofing and bonding are required, for example on wooden kitchen working benches, one of two procedures may be followed:

- spread **Keralastic** on the substrate with a flat trowel to a thickness of at least 2 mm; then rework the surface with a notched trowel so as to line it all over, but without reducing the thickness to less than 1 mm. This thickness must be maintained even after the tiles have been installed, especially when the tile backs have high lugs or ribs;
- spread **Keralastic** with a flat trowel to a uniform thickness of 1 mm for waterproofing and, after hardening (in any case within 24 hours), apply a second layer of **Keralastic** with a notched trowel.

Installing the tiles

Tiles must be absolutely dry. Place firm pressure to the tiles to ensure good contact and covering of the back. If the layer of fresh **Keralastic** or **Keralastic T** is also to act as a waterproofing membrane, make sure that any ribs and lugs do not go through the layer.

If **Keralastic** or **Keralastic T** is used for installing on particularly deformable substrates, all coverings larger than 5x5 cm must be installed with wide joints.

The open time of **Keralastic** and **Keralastic T** under normal temperature and moisture conditions is approximately 2 hours. Any adjustment must be carried out within 3 hours of installation.

The setting time is strictly tied to the ambient temperature (see table below).

Setting time of Keralastic and Keralastic T in relation to the temperature:

Temperature (°C)	30	25	20	15	10
Time (hours)	2	3	6	8	20

GROUTING AND SEALING

Joints between the tiles can be grouted after 12 hours with the appropriate MAPEI cementitious or epoxy grouts, available in different colours.

Expansion joints must be sealed with the special MAPEI sealants.

SET TO LIGHT FOOT TRAFFIC

Floors are set to light foot traffic after 12 hours.

READY FOR USE

Surfaces are ready for use after 7 days.

Cleaning

Tools, buckets and clothes can be easily cleaned with alcohol before hardening sets in. Hardened **Keralastic** can be cleaned mechanically or with **Pulicol**.

CONSUMPTION

Bonding of ceramics and stone material:

- Mosaics and small size tiles (trowel No. 4): 2.5 kg/m²
- Normal size tiles (trowel No. 5): 3.5 kg/m²
- Large size tiles, marble, stones (back buttering): 5 kg/m²

PACKAGING

Keralastic and **Keralastic T** are available in double metal drums of:

- 10 kg (9.4 kg/m² Part A + 0.6 kg/m² Part B);
- 5 kg (4.7 kg/m² Part A + 0.3 kg/m² Part B).

STORAGE

Keralastic and **Keralastic T** are stable for at least 24 months when stored in sealed drums. Part B (hardener) must be stored in warm place to avoid crystallisation during cold weather (at least at +10°C). Should crystallisation occur, re-dissolve by warming before use. Stir the product before use.



Laying on an old PVC floor



Waterproofing and laying in a prefabricated shower unit

TECHNICAL DATA (typical values)

In compliance with:

- European EN 12004 as R2, R2T
- American ANSI A 118.5 - 1999
- Canadian 71 GP 29 M

PRODUCT IDENTITY

	part A	part B
Consistency:	thick paste	fluid liquid
Colour:	Keralastic white - grey Keralastic T white - grey	straw transp. straw transp.
Density (g/cm³):	Keralastic 1.50 Keralastic T 1.56	0.93 0.93
Dry solid content (%):	97	100
Brookfield viscosity (mPa·s):	Keralastic 800000 (# F- rpm 2.5) Keralastic T 1800000 (# F- rpm 2.5)	26 (# 1- rpm 50) 46 (# 1- rpm 50)
Storage:	24 months in a dry place in original packaging. Store part A at least at +10°C to avoid crystallisation of the product, which is anyway reversible.	
Hazard classification according to EC 99/45:	irritant	corrosive
	Before using refer to the "Safety instructions for preparation and application" paragraph and the information on the packing and Safety Data Sheet	
Customs class:	3506 91 00	

APPLICATION DATA at +23°C and 50% R.H.

Mix ratio by weight:	part A : part B = 94 : 6	
Consistency of mix:	very viscous	
Density of mix (kg/m³):	Keralastic 1450 Keralastic T 1520	
Brookfield Viscosity (mPa·s):	Keralastic 400000 (# F - rpm 2.5) Keralastic T 800000 (# F - rpm 2.5)	
Pot life:	30-40 minutes	
Application temperature range:	from +10°C to +30°C	
Open time (according to EN 1346):	50 minutes	
Adjustability time:	90 minutes	
Setting time:		
- initial:	6 hours	
- final:	8 hours	
Set to light foot traffic:	12 hours	
Ready for use:	7 days	

FINAL PERFORMANCES

Shear adhesion strength according to EN 12003 (N/mm²):	
- initial shear adhesion strength:	2.6
- shear adhesion strength after water immersion:	2.0
- shear adhesion strength after thermal shock:	2.4
Resistance to ageing:	high
Resistance to solvents and oils:	good
Resistance to acids and alkalis:	good
Resistance to temperature:	from -40°C to +100°C
Deformability:	highly deformable



Installing Carrara marble on wooden substrate with White Keralastic



Green "Alpi" marble flooring in the Rolex building hall (Bienne - Switzerland)



An example of an installation of ceramic or marble on a metal structure (stairs)

Keralastic Keralastic T



Waterproofed bath-tub and shower

SAFETY INSTRUCTIONS FOR PREPARATION AND INSTALLATION

Keralastic and Keralastic T part A is irritating in direct contact with eyes and skin and a skin sensitiser.

Keralastic and Keralastic T part B is a strongly caustic and harmful substance in direct contact with the skin and if swallowed. Avoid any type of contact with the skin by always wearing protective gloves when using the product. When adding part B and during mixing wear protective gloves and goggles. In case of contact with the skin, wash with plenty of water and soap and if there should be any sensitivity of the skin, consult a doctor. In case of contact with the eyes, wash with plenty of water and consult a doctor.

Keralastic and Keralastic T are dangerous for aquatic organisms: do not release into the environment.

FOR PROFESSIONALS.

WARNING

Although the technical details and recommendations contained in this product report correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

All relevant references of the product are available upon request



BUILDING THE FUTURE

MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)



MAPEI S.p.A. - ITALY



MAPEI SUISSE SA

MAPEI KIL. - HUNGARY

MAPEI s.r.o. - CZECH REP.

MAPEI CORP. - U.S.A.

MAPEI INC - CANADA

MAPEI FAR EAST Pte Ltd

MAPEI ARGENTINA S.A.



MAPEI FRANCE

RESCON MAPEI AS - NORWAY

www.mapei.com

